



AMERICAN PETROLEUM INSTITUTE

Audit EP2014-0992

Audit - U.S. GLOBAL PETROLEUM - EVEREST FULL SYN

Engine Oils licensed under API's Engine Oil Licensing and Certification System (EOLCS) are purchased in the marketplace annually and audited to ensure the oils conform to program requirements. Audit candidates may be purchased in containers or drawn from bulk tanks (for example, those found at oil-change locations, service stations, and automotive service facilities). These candidates are chosen from a randomly-generated list of API-licensed oils, or, in the case of bulk engine oils, are purchased from randomly-selected locations.

The licensed oils collected from the marketplace undergo a series of bench tests to ensure the oils meet the performance requirements specified in API Publication 1509 and the EOLCS Application for Licensure. Additionally, the labels from licensed oils purchased in containers are examined to make sure the API Marks—the API Service Symbol “donut” and Certification Mark “Starburst”—are properly displayed and convey accurate information to consumers. All information regarding the collection and examination of the sample, including receipts, images and other documentation, can be found by expanding the ‘Collection Company Results’ section.

API has completed our analysis of the product indicated below. We are pleased to report that this oil complies with the requirements of API's Engine Oil Program and no further action on your part is required at this time.

API appreciates the actions that you have taken to ensure that this product satisfies the requirements of the EOLCS program.

Audit Information

Status: Complete
Brand Name: [EVEREST FULL SYN](#)
Viscosity Grade: 5W-30
Service Category & Designation: SN Resource Conserving, ILSAC GF-5
Due Date: N/A
Blind Sample ID: EP2014-0992
Sample Type: Packaged
Date Sample Taken: 26-Aug-2014
Sample Trace Code: patch#12306 mfg. 07-05-2014

Audit Information

Status: Complete
Brand Name: [EVEREST FULL SYN](#)
Viscosity Grade: 5W-30
Service Category & Designation: SN Resource Conserving, ILSAC GF-5
Due Date: N/A
Blind Sample ID: EP2014-0992
Sample Type: Packaged
Date Sample Taken: 26-Aug-2014
Sample Trace Code: patch#12306 mfg. 07-05-2014

Collection Company Results

Marketer Name: U.S. GLOBAL PETROLEUM, INC.
Brand Name: EVEREST FULL SYN
Viscosity: 5W-30
Service Category: SN
Test Protocol: PC46
CI-4 Plus Claimed: No
Quantity Collected: 5qts
Date Purchased: 26-Aug-2014
Purchased Location Name: Oil Depot
Purchased Location Type: 1
Purchased Address:
3357 Belt Line
Garland, TX 75044
United States
Traceability Code 1: patch#12306 mfg. 07-05-2014
Donut
Present: Yes
Similar To Donut: No
Outside Diameter: 2.42
Inside Diameter: 1.28
Ratio Value: 1.9
Ratio Conformance: Yes
Content: Yes
Content Comments:
Contrast: Yes
Contrast Comments:
General Comments:

Starbust
Starbust Present: Yes
Similar To Starburst: No
Outside Diameter: 2.38
Inside Diameter: 1.6
Ratio Value: 1.5
Ratio Conformance: Yes
Size Conformance: Yes
Content: Yes
Content Comments:
Contrast: Yes
Contrast Comments:
Location: Yes
Location Comments:
General Comments:
Collection Files
EP2014-0992 FOR1.pdf
EP2014-0992 LabelBack.jpg
EP2014-0992 LabelFront.jpg
EP2014-0992 Rcpt.pdf

Collection Company Results

Marketer Name: U.S. GLOBAL PETROLEUM, INC.
Brand Name: EVEREST FULL SYN
Viscosity: 5W-30
Service Category: SN
Test Protocol: PC46
CI-4 Plus Claimed: No
Quantity Collected: 5qts
Date Purchased: 26-Aug-2014
Purchased Location Name: Oil Depot
Purchased Location Type: 1
Purchased Address:
3357 Belt Line
Garland, TX 75044
United States
Traceability Code 1: patch#12306 mfg. 07-05-2014
Donut
Present: Yes
Similar To Donut: No
Outside Diameter: 2.42
Inside Diameter: 1.28
Ratio Value: 1.9
Ratio Conformance: Yes
Content: Yes
Content Comments:
Contrast: Yes
Contrast Comments:
General Comments:
Starbust
Starbust Present: Yes

Similar To Starburst: No
 Outside Diameter: 2.38
 Inside Diameter: 1.6
 Ratio Value: 1.5
 Ratio Conformance: Yes
 Size Conformance: Yes
 Content: Yes
 Content Comments:
 Contrast: Yes
 Contrast Comments:
 Location: Yes
 Location Comments:
 General Comments:
 Collection Files

EP2014-0992 FOR1.pdf
 EP2014-0992 LabelBack.jpg
 EP2014-0992 LabelFront.jpg
 EP2014-0992 Rcpt.pdf

Results Received

Test	Method	Reported	1509 Range	Expanded Range	Quick Test	Primary Test	Retest 1	Retest 2	Referee Test	Flag
Visc @ 100C - ASTM D445	ASTM D445	10.9	9.30 - 12.49	9.23 - 12.58	*	10.49*	*	*	*	
CCS @ -30C - ASTM D5293	ASTM D5293	6300	<= 6600	<= 7082	*	4860*	*	*	*	
MRV_Pumping @ -35C - ASTM D4684	ASTM D4684	25000	<= 60000	<= 81480	*	16600*	*	*	*	
MRV_Yield Stress - ASTM D4864	ASTM D4684		< 0	< 35	*	<35*	*	*	*	
HT/HS - ASTM D4683	ASTM D4683	3.1	>= 2.90	>= 2.80	*	3.07*	*	*	*	
NOACK - ASTM D5800_Method B	ASTM D5800_Method B	15	<= 15.00	<= 16.01	*	9.3*	*	*	*	
HT Foam-Stab - ASTM D6082	ASTM D6082		<= 0	<= 40	*	0*	*	*	*	
HT Foam-Tend - ASTM D6082	ASTM D6082		<= 100	<= 210	*	110*	*	*	*	
Zinc_Zn	ASTM D4951	0.085	0.0765 - 0.0978	0.0710 - 0.1048	*	0.0847*	*	*	*	
Calcium_Ca	ASTM D4951	0.214	0.1926 - 0.2461	0.1859 - 0.2547	*	0.2101*	*	*	*	
Magnesium_Mg	ASTM D4951		<= 0.0001	<= 0.0040	*	0.0011*	*	*	*	

Test	Method	Reported	1509 Range	Expanded Range	Quick Test	Primary Test	Retest 1	Retest 2	Reference Test	Flag
Sodium_Na	ASTM D4951		<= 0.0010	<= 0.0030	*	<0.0001*	*	*	*	
Titanium_Ti	ASTM D4951		<= 0.0001	<= 0.0020	*	<0.0001*	*	*	*	
Nitrogen_N - ASTM D5762	ASTM D5762	0.102	0.0918 - 0.1173	0.0679 - 0.1478	*	0.085*	*	*	*	
Boron_B	ASTM D4951	0.023	0.0207 - 0.0265	0.0172 - 0.0300	*	0.0233*	*	*	*	
Molybdenum_Mo	ASTM D4951	0.0079	0.0067 - 0.0095	0.0056 - 0.0111	*	0.0082*	*	*	*	
Phosphorus_P	ASTM D4951	0.077	0.0600 - 0.0800	0.0540 - 0.0880	*	0.0771*	*	*	*	
Sulfur_S - ASTM D4951	ASTM D4951	0.3	<= 0.5000	<= 0.5610	*	0.2925*	*	*	*	
Total Base Number - ASTM D2896	ASTM D2896	7.9	7.11 - 9.09	6.61 - 9.72	*	7.9*	*	*	*	
Aluminum_Al	ASTM D4951				*	0.0002*	*	*	*	
Copper_Cu	ASTM D4951				*	<0.0001*	*	*	*	
Silicon_Si	ASTM D4951				*	0.0005*	*	*	*	
Silver_Ag	ASTM D4951				*	<0.0001*	*	*	*	
Barium_Ba	ASTM D4951				*	<0.0001*	*	*	*	
Cadmium_Cd	ASTM D4951				*	<0.0001*	*	*	*	
Chromium_Cr	ASTM D4951				*	<0.0001*	*	*	*	
Iron_Fe	ASTM D4951				*	<0.0001*	*	*	*	
Potassium_K	ASTM D4951				*	<0.0001*	*	*	*	
Manganese_Mn	ASTM D4951				*	<0.0001*	*	*	*	
Nickel_Ni	ASTM D4951				*	<0.0001*	*	*	*	
Lead_Pb	ASTM D4951				*	<0.0001*	*	*	*	
Antimony_Sb	ASTM D4951				*	<0.0001*	*	*	*	
Tin_Sn	ASTM D4951				*	<0.0001*	*	*	*	

Test	Method	Reported	1509 Range	Expanded Range	Quick Test	Primary Test	Retest 1	Retest 2	Reference Test	Flag
Vanadium_V	ASTM D4951				*	<0.0001*	*	*	*	

Results Received

Test	Method	Reported	1509 Range	Expanded Range	Quick Test	Primary Test	Retest 1	Retest 2	Reference Test	Flag
Visc @ 100C - ASTM D445	ASTM D445	10.9	9.30 - 12.49	9.23 - 12.58	*	10.49*	*	*	*	
CCS @ -30C - ASTM D5293	ASTM D5293	6300	<= 6600	<= 7082	*	4860*	*	*	*	
MRV_Pumping @ -35C - ASTM D4684	ASTM D4684	25000	<= 60000	<= 81480	*	16600*	*	*	*	
MRV_Yield Stress - ASTM D4864	ASTM D4684		< 0	< 35	*	<35*	*	*	*	
HT/HS - ASTM D4683	ASTM D4683	3.1	>= 2.90	>= 2.80	*	3.07*	*	*	*	
NOACK - ASTM D5800_Method B	ASTM D5800_Method B	15	<= 15.00	<= 16.01	*	9.3*	*	*	*	
HT Foam-Stab - ASTM D6082	ASTM D6082		<= 0	<= 40	*	0*	*	*	*	
HT Foam-Tend - ASTM D6082	ASTM D6082		<= 100	<= 210	*	110*	*	*	*	
Zinc_Zn	ASTM D4951	0.085	0.0765 - 0.0978	0.0710 - 0.1048	*	0.0847*	*	*	*	
Calcium_Ca	ASTM D4951	0.214	0.1926 - 0.2461	0.1859 - 0.2547	*	0.2101*	*	*	*	
Magnesium_Mg	ASTM D4951		<= 0.0001	<= 0.0040	*	0.0011*	*	*	*	
Sodium_Na	ASTM D4951		<= 0.0010	<= 0.0030	*	<0.0001*	*	*	*	
Titanium_Ti	ASTM D4951		<= 0.0001	<= 0.0020	*	<0.0001*	*	*	*	
Nitrogen_N - ASTM D5762	ASTM D5762	0.102	0.0918 - 0.1173	0.0679 - 0.1478	*	0.085*	*	*	*	
Boron_B	ASTM D4951	0.023	0.0207 - 0.0265	0.0172 - 0.0300	*	0.0233*	*	*	*	
Molybdenum_Mo	ASTM D4951	0.0079	0.0067 - 0.0095	0.0056 - 0.0111	*	0.0082*	*	*	*	
Phosphorus_P	ASTM D4951	0.077	0.0600 - 0.0800	0.0540 - 0.0880	*	0.0771*	*	*	*	

Test	Method	Reported	1509 Range	Expanded Range	Quick Test	Primary Test	Retest 1	Retest 2	Reference Test	Flag
Sulfur_S - ASTM D4951	ASTM D4951	0.3	<= 0.5000	<= 0.5610	*	0.2925*	*	*	*	
Total Base Number - ASTM D2896	ASTM D2896	7.9	7.11 - 9.09	6.61 - 9.72	*	7.9*	*	*	*	
Aluminum_Al	ASTM D4951				*	0.0002*	*	*	*	
Copper_Cu	ASTM D4951				*	<0.0001*	*	*	*	
Silicon_Si	ASTM D4951				*	0.0005*	*	*	*	
Silver_Ag	ASTM D4951				*	<0.0001*	*	*	*	
Barium_Ba	ASTM D4951				*	<0.0001*	*	*	*	
Cadmium_Cd	ASTM D4951				*	<0.0001*	*	*	*	
Chromium_Cr	ASTM D4951				*	<0.0001*	*	*	*	
Iron_Fe	ASTM D4951				*	<0.0001*	*	*	*	
Potassium_K	ASTM D4951				*	<0.0001*	*	*	*	
Manganese_Mn	ASTM D4951				*	<0.0001*	*	*	*	
Nickel_Ni	ASTM D4951				*	<0.0001*	*	*	*	
Lead_Pb	ASTM D4951				*	<0.0001*	*	*	*	
Antimony_Sb	ASTM D4951				*	<0.0001*	*	*	*	
Tin_Sn	ASTM D4951				*	<0.0001*	*	*	*	
Vanadium_V	ASTM D4951				*	<0.0001*	*	*	*	